



golden power

KR240AAA2

**TECHNICAL SPECIFICATION
FOR
SEALED Ni-CD CYLINDRICAL BATTERY**

PREPARED BY : Xie Hong Chao
APPROVED BY : Cecilia Chu
DATE : 4-Oct-01
SPEC. NO. : S-KR240AAA2-B

GOLDEN POWER INDUSTRIES LTD.

Flat C, 20/F, Block 1, Tai Ping Industrial Centre, 57 Ting Kok Road, Tai Po, N.T., Hong Kong.

Tel: (852) 3125 2288 Fax: (852) 3125 2000 / (852) 3125 2001

E-mail: battery@goldenpower.com Web Page: <http://www.goldenpower.com>

1. Scope

This specification applies to sealed nickel cadmium cylindrical rechargeable single cell, KR240AAA2 and stack up battery packs. All the data involving voltage and weight of stack up battery packs equal to the value of single cell times the number of single cell in the battery packs.

2. Cell Type

Golden Power Designation: KR240AAA2
 Size: AAA
 IEC Designation: KR 03


3. Rating

Nominal Voltage: 1.2V
 Nominal Capacity: 240mAh
 Internal Impedance: Max. $\leq 46 \text{ m}\Omega$ (after fully charged)
Normal Charge Current: 24 mA (0.1C) at 0°C ~ 45°C
Normal Charge Duration: 14~16 hrs
Quick Charge Current: 240 mA (1C) at 10°C ~ 45°C
Quick Charge Duration: 1.5 hrs
Trickle Charge Current: ~ NA ~
 Discharge Temperature: -20°C ~ 60°C

4. Physical Specification

The dimensions of a single sealed nickel cadmium cylindrical rechargeable cell, KR240AAA2, are shown in Table I. The PVC jacket comes within these tolerances.

Table I. Dimensions of KR240AAA2

Cell Drawing	Cell Dimensions (mm)	
 <p>The drawing shows a cylindrical cell with a diameter dimensioned as $\varnothing 10.1$ and a height dimensioned as 43.0.</p>	Diameter	$\varnothing 10.1$
	Height	43 mm
	Jacket	PVC
	Weight	10 g

5. Electrical Specifications

5.1 Charging procedure for test purpose

The cell shall be charged at an ambient temperature of $20\pm 5^{\circ}\text{C}$ at a constant current of **24mA (0.1C) for 15 hours**.

5.2 Discharging test

The cell shall be charged according to 5.1 prior the test, and shall be stored for not less than 1 hour and not more than 4 hours at an ambient temperature of $20\pm 5^{\circ}\text{C}$ and relative humidity of $65\pm 20\%$. At the same ambient temperature, the cell shall be discharged at various rate, and the available rated capacity shall meet the standard specified in *Table II.* within five cycles.

Table II. Discharge Test at 20°C

Constant Discharge Current	Constant Discharge Current Rate (C)	End Point Voltage (V)	Discharge Duration ¹⁾	Available Capacity (%) ¹⁾
48mA	0.2	1.0	5 hr	100
120mA	0.5	1.0	108 min	90

¹⁾ Minimum Values

5.3 Charge retention

In the charge retention test, the cell shall be charged according to 5.1, and shall be stored in open circuit for 28 days at an average ambient temperature of $20\pm 5^{\circ}\text{C}$ and relative humidity of $65\pm 20\%$. After the storage, the cell shall be discharged at the same ambient temperature according to the *standard discharge* stated in 5.2. The capacity of the cell shall not be less than **180mAh (75%)**.

6. Storage Recommendation

The battery can be stored at a temperature range of $-20^{\circ}\text{C} \sim 60^{\circ}\text{C}$ for normal storage and $-30^{\circ}\text{C} \sim 40^{\circ}\text{C}$ for prolonged storage, and at a maximum relative humidity of 85%.

7. Cycle Life

Cycle life test is a series of charge-discharge test cycles, and the cycle life is defined as the number of cycle tested until the available capacity drops down to 60% of nominal capacity. The cycle life of the cell shall not be less than 500.

8. Precautions

- Do not throw the cells / batteries into fire or attempt to disassemble them.
- Do not have direct spot welding to the cells / batteries.
- Do not short circuit the cells / batteries.
- Do not use same size primary batteries together with Ni-CD battery.
- Do not use discharged and charged Ni-CD batteries together.
- Keep Charging temperature and rate within our recommended limits.

9. Golden Power reserves the right to modify product specification and data stated herein without prior notice.