



# MR1500AA2

---

## TECHNICAL SPECIFICATION FOR SEALED Ni-MH CYLINDRICAL BATTERY

DATE : 15-Jul-2001  
SPEC. NO. : S-MR1500AA2-2005A

---

### **GOLDEN POWER CORPORATION (HK) LTD.**

Flat C, 20/F, Block 1, Tai Ping Industrial Centre, 57 Ting Kok Road, Tai Po, N.T., Hong Kong.

Tel: (852) 3125 2288 Fax: (852) 3125 2000 / (852) 3125 2001

E-mail: [battery@goldenpower.com](mailto:battery@goldenpower.com) Web Page: <http://www.goldenpower.com>

---

### 1. Scope

This specification applies to sealed nickel metal-hydride cylindrical rechargeable single cell, MR1500AA2 and stack up battery packs. All the data involving voltage and weight of stack up battery packs equal to the value of single cell times the number of single cell in the battery packs.

### 2. Cell Type

Golden Power Designation: MR1500AA2  
 Size: AA  
 IEC Designation: HR 06


### 3. Rating

Nominal Voltage: 1.2V  
 Nominal Capacity: 1500mAh  
 Internal Impedance: Max.  $\leq 25$  m $\Omega$  (after fully charged)  
**Normal** Charge Current: 150 mA (0.1C) at 0°C ~ 45°C  
**Normal** Charge Duration: 14~16 hrs  
**Quick** Charge Current: 750 mA (0.5C) at 10°C ~ 40°C  
**Quick** Charge Duration: 2.5 hrs  
**Trickle** Charge Current: ~ NA ~  
 Discharge Temperature: -20°C ~ 60°C

### 4. Physical Specification

The dimension of a rechargeable nickel metal-hydride cylindrical cell, MR1500AA2 are shown in Table I. The PVC jacket comes within these tolerances.

Table I. Dimensions of MR1500AA2

Cell Drawing	Cell Dimensions (mm)	
	Diameter	Ø14.5 +0.0/-0.7
	Height	49 +0.0/-1.0
	Jacket	PVC
	Weight (For Ref. Only)	27 g

**5. Electrical Specifications**

**5.1 Charging procedure for test purpose**

The cell shall be charged at an ambient temperature of 20±5 °C at a constant current of 150mA (0.1C) for 15 hours.

**5.2 Discharging test**

The cell shall be charged according to 5.1 prior to the test, and shall be stored for not more than 1 hour at an ambient temperature of 20±5 °C and relative humidity of 65±20%.

At the same ambient temperature, the cell shall be discharged at various rate, and the available rated capacity shall meet the standard specified in *Table II.* within five cycles.

*Table II. Discharge Test at 20 °C*

Constant Discharge Current	Constant Discharge Current Rate (C)	End Point Voltage (V)	Discharge Duration <sup>1)</sup>	Available Capacity (%) <sup>1)</sup>
300mA	0.2	1.0	5 hr	100
750mA	0.5	1.0	108 min	90

<sup>1)</sup> Minimum Values

**5.3 Charge retention**

In the charge retention test, the cell shall be charged according to 5.1 , and shall be stored in open circuit for 28 days at an average ambient temperature of 20±5 °C and relative humidity of 65±20%. After the storage, the cell shall be discharged at the same ambient temperature according to the *standard discharge* stated in 5.2 . The capacity of the cell shall not be less than 975mAh (65%).

**6. Storage Recommendation**

The battery can be stored at a temperature range of -20°C ~ 35°C for normal storage and -20°C ~ 35°C for prolonged storage, and at a maximum relative humidity of 85%.

One recovery charging (ref to 5.1) is recommended for every 6 months of storage, in order to protect the cell quality performance.

**7. Cycle Life**

Cycle life test is a series of charge-discharge test cycles, and the cycle life is defined as the number of cycle tested until the available capacity drops down to 60% of nominal capacity.

The cycle life of the cell shall not be less than 500.

**8. Precautions**

- Do not throw the cells / batteries into fire or attempt to disassemble them.
- Do not have direct spot welding to the cells / batteries.
- Do not short circuit the cells / batteries.
- Do not use same size primary batteries together with Ni-MH battery.
- Do not use discharged and charged Ni-MH batteries together.
- Keep charging temperature and rate within our recommended limits.

- 9.** Golden Power reserves the right to modify product specification and data stated herein without prior notice.